

Coating for High Temperature Acid Immersion



BELZONA[®]
1392



Belzona 1392 (Ceramic HT2) is a two component high temperature coating system designed to resist hydrocarbons and aqueous solutions. This product was specifically designed to exhibit excellent chemical resistance, particularly in systems contaminated by acid. It also provides excellent erosion resistance.

Belzona 1392 (Ceramic HT2) can operate continuously in immersed conditions at temperatures up to 120°C (248°F). It also has excellent resistance to process chemicals and conditions such as steam out and rapid depressurisation.

TECHNICAL DATA	Mixing ratio (base:solidifier)	20 : 1 by weight
	Working life	35 minutes at 20°C (68°F)
	Shelf life	2 years
	Dry heat resistance	230°C (446°F)
	Adhesion (tensile shear)	Mild steel: 18.13 MPa (2,630 psi) at 20°C (68°F) cure
	Compressive strength	102.04 MPa (14,800 psi) at 20°C (68°F) cure
	Volume capacity	439 cm ³ (26.8 in ³) / 1 kg
	Heat distortion temperature	49°C (118°F) at 20°C (68°F) cure
	Coverage rate	0.73 m ² (7.9 ft ²) / 1 kg at 600 microns (24 mils)
	Abrasion resistance	H10 - 145 mm ³ 100°C (212°F) cure, wet

CURE TIMES	Temperature	20°C (68°F)	30°C (86°F)	40°C (104°F)
	Time until inspection	12 hours	5 hours	3 hours
	Time until full service	96 hours	18 hours	10 hours
	Time until dry post cure (if required)	12 hours	5 hours	3 hours
	Time until wet post cure (if required)	28 hours	8 hours	5 hours

*Please consult the Product Specification Sheet (PSS) and Instructions for Use (IFU) for the latest technical data.




**HIGH
TEMPERATURE
RESISTANT**



CHEMICAL RESISTANT



SOLVENT-FREE



**HIGH COMPRESSIVE
STRENGTH**



**SIMPLE
APPLICATION**

Key Benefits:

- Excellent resistance to corrosion**
 This coating is specially designed to provide erosion-corrosion protection in acid contaminated water/hydrocarbon systems.
- High chemical resistance**
 This material resists water, aqueous solutions, hydrocarbons in acid contaminated water and hydrocarbons up to temperatures of 120°C (248°F) in continuous immersion.
- Simple application**
 This easy to use epoxy coating can be applied by brush or applicator eliminating the need for specialist tools and will cure at room temperature.

Application Examples:



Screw conveyors protected



Engine block coated

Application Areas:

- Condensate extraction pumps
- Condensate return tanks
- Evaporators
- Heat exchanger barrels
- Separators
- Autoclaves
- Scrubber units
- Rotary reactor
- Calorifiers
- Distillation units
- Slug catchers
- Absorber towers

Key

Excellent	Ex	No significant deterioration / barrier properties retained for greater than 52 weeks. Suitable for all applications including long term immersion
Good	G	No significant deterioration / barrier properties retained for 12-52 weeks. Suitable for short short-term immersion and general chemical contact
Moderate	M	No significant deterioration / barrier properties retained for 1-12 weeks. Suitable for applications involving short term chemical contact e.g. spillage, splash or secondary containment
*	Ex	Product must be post cured to deliver quoted chemical resistance

Inorganic Acids

Chemical name (synonym)	Chemical Formula (synonym)	Concentration	Chemical Resistance	
			20°C 68°F	60°C 140°F
Hydrochloric acid	HCL	36%	G*	G
		20%	Ex*	G
		10%	Ex*	G
		5%	Ex	Ex
		3%	Ex	Ex
Nitric acid	HNO ₃	20%	Ex*	M
		10%	Ex*	G
		5%	Ex*	G
Nitrous acid	HNO ₂	20%	Ex*	M
		40%	Ex*	G
Phosphoric acid	H ₃ PO ₄	20%	Ex*	G
		10%	Ex*	Ex
		5%	Ex*	Ex
		98%	G*	M
Sulphuric acid	H ₂ SO ₄	70%	Ex*	Ex
		50%	Ex*	Ex
		30%	Ex*	Ex
		20%	Ex	Ex
		10%	Ex*	Ex
		5%	Ex	Ex

For more information, please contact your local Belzona representative:

QUALITY PRODUCTS - TECHNICAL SUPPORT

Belzona products are manufactured under an ISO 9001 Registered Quality Management System.

Belzona has a global distribution network of over 140 Distributors operating in 120 countries. Local support is provided by a trained Technical Consultant who will diagnose the problem, recommend the solution and provide 24-hour, on-site application supervision and advice.